



Technical Properties

Physical	Unit	Test Method	Result
Specific gravity	g/cm ³	DIN EN ISO 1183-1	0.94
Water absorption till saturation 23°C	%	DIN EN ISO 62	
Maximum service temp. Upper temp limit - short term	°C		100
Maximum service temp. Upper temp limit - Long term	°C		80
Lower temp limit	°C		-100
Mechanical	Unit	Test Method	Result
Tensile strength	MPa	DIN EN ISO 527-1	≥ 24
Elongation at yield	%	DIN EN ISO 527-1	200
Unnotched Impact strength	kJ/m ²	DIN EN ISO 179-1	no break
Notch impact strength	kJ/m ²	DIN EN ISO 179-1	> 140
Ball indentation / Rockwell hardness	MPa	DIN EN ISO 2039-1	38
Shore-D		DIN EN ISO 868	62 - 65
Tensile modulus of elasticity	MPa	DIN EN ISO 527-1	800
Thermal	Unit	Test Method	Result
Vicat-softening point VST/B/50	°C	DIN EN ISO 306	80
Coefficient of linear thermal expansion 23°C - 100°C	m/(m.K)	ISO 11359-2	1.5-2·10 ⁻⁴
Thermal conductivity at 23°C	W/mK	ISO 52612	> 0.40
Electrical	Unit	Test Method	Result
Surface resistivity	Ω	DIN EN 62631-3-1	<10 ⁹
Additional Data	Unit	Test Method	Result
Food compliance - FDA		FDA	no
Food compliance - EU		EU 10/2011	no
Antistatic			yes
Flammability	Unit	Test Method	Result
Fire performance		UL 94	HB
Optical	Unit	Test Method	Result

All information is for guide purposes only. The data has been taken from standard test results provided by our manufacturers.



T: +44 (0) 116 289 3343 E: info@facadecreations.co.uk W: www.facadecreations.co.uk

Registered Office Address: 124 City Road, London, England, EC1V 2NX

Registered in England, Company Number: 16267073