



Technical Properties

Physical	Unit	Test Method	Result
Specific gravity	g/cm ³	ASTM 1183	0.91
Mechanical	Unit	Test Method	Result
Tensile strength at break	MPa	ASTM 527/2	20
Notch impact strength	kJ/m ²	ASTM 180A	17
Shore-D		ASTM 868	60
Flexural modulus of elasticity	MPa	ASTM 178	1200
Thermal	Unit	Test Method	Result
Heat deflection temperature HDT/B	°C	ASTM 78/B	70
Electrical	Unit	Test Method	Result
Additional Data	Unit	Test Method	Result
Flammability	Unit	Test Method	Result
Optical	Unit	Test Method	Result

All information is for guide purposes only. The data has been taken from standard test results provided by our manufacturers.



T: +44 (0) 116 289 3343 E: info@facadecreations.co.uk W: www.facadecreations.co.uk

Registered Office Address: 124 City Road, London, England, EC1V 2NX

Registered in England, Company Number: 16267073