

### Chemical Designation

PC (Polycarbonate)

### Colour

natural transparent

### Density

1.23 g/cm<sup>3</sup> (\*2)

### Fillers

flame retardant (halogen free)

### Main features

- electrically insulating
- good weldable and bondable
- tested according to EN 45545
- flame retardant as per FAR 25.853
- flame retardant according to UL94 V-0

### Target Industries

- electronics
- Railway Interiors
- automotive industry
- mechanical engineering
- aircraft and aerospace interiors
- aircraft and aerospace technology

General material information	parameter	value	unit	norm	comment
Diameter		2,85 +/- 0,05	mm	-	(1) standard spool body
Spool measurements	outer diameter	Ø 200	mm	-	(2) Ø 2,85mm
Spool measurements	width	55	mm	-	
Spool measurements	holder	Ø 52	mm	-	
Spool Material		Polycarbonate		-	
Filament Load per Spool		750	g	-	
Filament Length per Spool		92	m	-	2)

Mechanical properties	parameter	value	unit	norm	comment
Tensile strength	5mm/min, Orientation XY	69	MPa	DIN EN ISO 527-2	1) (1) (*5), (*6)
Tensile strength	5mm/min, Orientation ZX	34	MPa	DIN EN ISO 527-2	2) (2) (*5), (*6)
Modulus of elasticity (tensile test)	5mm/min, Orientation XY	2750	MPa	DIN EN ISO 527-2	3) (3) (*5), (*6)
Modulus of elasticity (tensile test)	5mm/min, Orientation ZX	2800	MPa	DIN EN ISO 527-2	4) (4) (*5), (*6)
Elongation at break (tensile test)	5mm/min, Orientation XY	3,8	%	DIN EN ISO 527-2	5) (5) (*5), (*6)
Elongation at break (tensile test)	5mm/min, Orientation ZX	1,4	%	DIN EN ISO 527-2	6) (6) (*5), (*6)
Flexural strength	5mm/min, Orientation XY	105	MPa	DIN EN ISO 178	7) (7) (*5), (*6)
Flexural strength	5mm/min, Orientation ZX	67	MPa	DIN EN ISO 178	8) (8) (*5), (*6)
Modulus of elasticity (flexural test)	5mm/min, Orientation XY	2750	MPa	DIN EN ISO 178	9) (9) (*5), (*6)
Modulus of elasticity (flexural test)	5mm/min, Orientation ZX	3300	MPa	DIN EN ISO 178	10) (10) (*5), (*6)
Elongation at break (flexural test)	5mm/min, Orientation XY	3,9	%	DIN EN ISO 178	11) (11) (*5), (*6)
Elongation at break (flexural test)	5mm/min, Orientation ZX	1,8	%	DIN EN ISO 178	12) (12) (*5), (*6)

Thermal properties	parameter	value	unit	norm	comment
Glass transition temperature		80	°C	ASTM D 3418	1) (1) (*2)
Melting temperature		-		DIN EN ISO 11357	2) (2) (*2)
Deflection temperature	HDT-A	69	°C	ISO-R 75 Method A	3) (3) (*5), (*6)
Service temperature	short term	70	°C	-	4) (4) (*2)
Service temperature	long term	60	°C	-	5) (5) (*2)
Thermal expansion (CLTE)		-	10 <sup>-5</sup> K <sup>-1</sup>	DIN EN ISO 11359-1;2	6) (6) (*2)

Other properties	parameter	value	unit	norm	comment
Moisture absorption		0,14	%	DIN EN ISO 62	(1) (*5), (*6)
Flammability (UL94)	125x13x1,5mm; Orientation XY	V0		DIN IEC 60695-11-10;	1) (2) (*5), (*6)
Flammability (UL94)	125x13x5,0mm; Orientation XY	V0		DIN IEC 60695-11-10;	2) (3) (*5), (*6)
Flammability	s=1,5mm & s=10mm	R22 HL3, R23 HL3,		EN 45545-2:2016	3) (4) (*5), (*6)
Flammability	60 sec. Vertical Bunsen Burner test, FAR §25.853 (a) and Appendix F, Part I, para. (a)(1)(i)	1,5	mm	FAR 25.853	4) (5) (*5), (*6)
Flammability	12 sec. Vertical Bunsen Burner test, FAR §25.853 (a) and Appendix F, Part I, para. (a)(1)(ii)	1,5	mm	FAR 25.853	5) (6) (*5), (*6)
Flammability	15 sec. Horizontal Bunsen Burner test, FAR §25.853 (a) and Appendix F, Part I, para. (a)(1)(iv)& (v)	1,5	mm	FAR 25.853	6) (7) (*5), (*6)
Flammability	Gas Toxicity, as per Boeing BSS 7239	1,5	mm	-	7)
Melt flow index (MFI)	300°C / 1,2kg	35,3	g/10 min	DIN EN ISO 1133	

Processing parameter	parameter	value	unit	norm	comment
Nozzle temperature		240 - 280	°C	-	(1) not required
Max. melt temperature		300	°C	-	
Print bed temperature		70 - 90	°C	-	

Build chamber temperature	-	-	-	-	1)
Nozzle diameter	0,4	mm	-	-	-
Print speed	30 - 50	mm/s	-	-	-
Fan speed	20 - 40	%	-	-	-
<i>Predrying</i>	<i>parameter</i>	<i>value</i>	<i>unit</i>	<i>norm</i>	<i>comment</i>
Drying temperature	60	°C	-	-	1) (*4)
Drying time	8	h	-	-	-

