

Chemical Designation
PEEK (Polyetheretherketone)

Colour
black opaque

Density
1.38 g/cm³ (*2)

Fillers
carbon fibres, 30% carbon fibres

Main features
→ very high stiffness
→ inherent flame retardant
→ high dimensional stability
→ good chemical resistance
→ hydrolysis and superheated steam resistant

Target Industries
→ oil and gas industry
→ automotive industry
→ chemical technology
→ mechanical engineering
→ aircraft and aerospace technology

| General material information | parameter | value | unit | norm | comment |
|------------------------------|----------------|---------------|------|------|---|
| Diameter | | 1,75 +/- 0,05 | mm | - | (1) standard spool body |
| Spool measurements | holder | Ø 52 | mm | - | (2) do not dry spool >120°C (3) Ø 1,75mm |
| Spool measurements | width | 55 | mm | - | |
| Spool measurements | outer diameter | Ø 200 | mm | - | 1) |
| Spool Material | | Polycarbonate | - | - | 2) |
| Filament Load per Spool | | 500 | g | - | |
| Filament Length per Spool | | 141 | m | - | 3) |

| Mechanical properties | parameter | value | unit | norm | comment |
|--------------------------------------|-------------------------|---------|-------------------|--------------------|--|
| Tensile strength | 5mm/min, Orientation XY | 173,7 | MPa | DIN EN ISO 527-2 | 1) (1) (*5), (*6) (2) (*5), (*6) |
| Tensile strength | 5mm/min, Orientation XZ | 198,5 | MPa | DIN EN ISO 527-2 | 2) (3) (*5), (*6) (4) (*5), (*6) |
| Tensile strength | 5mm/min, Orientation ZX | 61,9 | MPa | DIN EN ISO 527-2 | 3) (5) (*5), (*6) (6) (*5), (*6) |
| Modulus of elasticity (tensile test) | 5mm/min, Orientation XY | 18116,0 | MPa | DIN EN ISO 527-2 | 4) (7) (*5), (*6) (8) (*5), (*6) |
| Modulus of elasticity (tensile test) | 5mm/min, Orientation XZ | 21392,0 | MPa | DIN EN ISO 527-2 | 5) (9) (*5), (*6) (10) (*5), (*6) |
| Modulus of elasticity (tensile test) | 5mm/min, Orientation ZX | 4005,5 | MPa | DIN EN ISO 527-2 | 6) (11) (*5), (*6) (12) (*5), (*6) (13) (*1) |
| Elongation at yield (tensile test) | 5mm/min, Orientation XY | 2,4 | % | DIN EN ISO 527-2 | 7) |
| Elongation at yield (tensile test) | 5mm/min, Orientation XZ | 2,1 | % | DIN EN ISO 527-2 | 8) |
| Elongation at yield (tensile test) | 5mm/min, Orientation ZX | 3,3 | % | DIN EN ISO 527-2 | 9) |
| Elongation at break (tensile test) | 5mm/min, Orientation XY | 2,4 | % | DIN EN ISO 527-2 | 10) |
| Elongation at break (tensile test) | 5mm/min, Orientation XZ | 2,2 | % | DIN EN ISO 527-2 | 11) |
| Elongation at break (tensile test) | 5mm/min, Orientation ZX | 3,3 | % | DIN EN ISO 527-2 | 12) |
| Impact strength (Charpy) | max. 7,5J - 23°C | 45,0 | kJ/m ² | DIN EN ISO 179-1eU | 13) |

| Thermal properties | parameter | value | unit | norm | comment |
|------------------------------|------------|-------|----------------------------------|----------------------|-------------------------|
| Glass transition temperature | | 143 | °C | ASTM D 3418 | 1) (1) (*2) (2) (*2) |
| Melting temperature | | 343 | °C | DIN EN ISO 11357 | 2) (3) (*2) (4) (*2) |
| Deflection temperature | HDT-A | 162 | °C | ISO-R 75 Method A | 3) (5) (*2) (6) (*2) |
| Service temperature | short term | 300 | °C | - | 4) |
| Service temperature | long term | 260 | °C | - | 5) |
| Thermal expansion (CLTE) | | 4 | 10 ⁻⁵ K ⁻¹ | DIN EN ISO 11359-1:2 | 6) |

| Other properties | parameter | value | unit | norm | comment |
|-----------------------|---|-------|----------|----------------------|---|
| Moisture absorption | | 0,03 | % | DIN EN ISO 62 | 1) (1) (*2) (2) (*2) |
| Flammability (UL94) | 125x13x1,5mm | V0 | | DIN IEC 60695-11-10; | 2) (3) (*5), (*6) (4) (*5), (*6) |
| Flammability | 60 sec. Vertical Bunsen Burner test, FAR §25.853 (a) and Appendix F, Part I, para. (a)(1)(i) | 1,4 | mm | FAR 25.853 | 3) (5) (*5), (*6) (6) (*5), (*6) (7) (*5), (*6) (8) (*5), (*6) |
| Flammability | 12 sec. Vertical Bunsen Burner test, FAR §25.853 (a) and Appendix F, Part I, para. (a)(1)(ii) | 1,4 | mm | FAR 25.853 | 4) (9) (*2) |
| Flammability | 15 sec. Horizontal Bunsen Burner test, FAR §25.853 (a) and Appendix F, Part I, para. (a)(1)(iv) | 1,5 | mm | FAR 25.853 | 5) |
| Flammability | Heat Release, as per FAR §25.853 (d) and Appendix F, Part IV | 1,6 | mm | FAR 25.853 | 6) |
| Flammability | Smoke density, as per FAR §25.853 (d) and Appendix F, Part V | 1,5 | mm | FAR 25.853 | 7) |
| Flammability | Gas Toxicity, as per Boeing BSS 7239 | 1,5 | mm | - | 8) |
| Melt flow index (MFI) | | - | g/10 min | DIN EN ISO 1133 | 9) |

| Processing parameter | parameter | value | unit | norm | comment |
|---------------------------|-----------|-----------|------|------|--------------|
| Nozzle temperature | | 420 - 460 | °C | - | (1) required |
| Max. melt temperature | | 470 | °C | - | |
| Print bed temperature | | 160 - 250 | °C | - | |
| Build chamber temperature | | 160 - 230 | °C | - | 1) |

| | | | | | |
|--------------------|------------------|--------------|-------------|-------------|----------------|
| Nozzle diameter | 0,4 - 0,6 | mm | - | | |
| Print speed | 20 - 30 | mm/s | - | | |
| Fan speed | 0 | % | - | | |
| <i>Predrying</i> | <i>parameter</i> | <i>value</i> | <i>unit</i> | <i>norm</i> | <i>comment</i> |
| Drying temperature | 120 | °C | - | 1) | (1) (*4) |
| Drying time | 8 | h | - | | |

