

Chemical Designation

PI (Polyimide)

Colour

black

Density

1.45 g/cm³

Fillers

15% graphite

Main features

- very good slide and wear properties
- very good thermal stability
- high thermal and mechanical capacity
- good wear resistance
- resistance against high energy radiation
- high creep resistance
- good chemical resistance
- sensitive to hydrolysis in higher thermal range

Target Industries

- mechanical engineering
- precision engineering
- automotive industry
- aircraft and aerospace technology
- cryogenic engineering
- conveyor technology
- hot glass technology

<i>Mechanical properties</i>	<i>parameter</i>	<i>value</i>	<i>unit</i>	<i>norm</i>	<i>comment</i>
Tensile strength	50 mm/min	101	MPa	DIN EN ISO 527-1	(1) eU (2) eA
Modulus of elasticity (tensile test)	1 mm/min	4400	MPa	DIN EN ISO 527-1	
Elongation at break (tensile test)	50 mm/min	4.5	%	DIN EN ISO 527-1	
Flexural strength	10 mm/min	145	MPa	DIN EN ISO 178	
Modulus of elasticity (flexural test)	2 mm/min	4000	MPa	DIN EN ISO 178	
Elongation at break (flexural test)	10 mm/min	4.6	%	DIN EN ISO 178	
Compression strength	10 mm/min	280	MPa	EN ISO 604	
Compression strength	10mm/min, 10% strain	160	MPa	EN ISO 604	
Compression modulus	1 mm/min	1900	MPa	EN ISO 604	
Compressive strain at break	10 mm/min	43	%	EN ISO 604	
Impact strength (Charpy)	max 7.5 J	36.7	kJ/m ²	DIN EN ISO 179-1	1)
Notched impact strength (Charpy)	max 7.5 J	2.9	kJ/m ²	DIN EN ISO 179-1	2)
Shore hardness	Shore D	87		DIN EN ISO 868	
<i>Thermal properties</i>	<i>parameter</i>	<i>value</i>	<i>unit</i>	<i>norm</i>	<i>comment</i>
Glass transition temperature		357	°C	-	1)
Heat distortion temperature	1.8 MPa	335	°C	DIN 53 461	(1) DMA, maximum loss factor tan d (2) Thermal expansion XYZ axis
Thermal expansion (CLTE)	50-200°C	3.8 / 4.5	10 ⁻⁵ K ⁻¹	DIN 53 752	2)
Thermal expansion (CLTE)	200-300°C	4.6 / 5.4	10 ⁻⁵ K ⁻¹	DIN 53 752	3)
<i>Other properties</i>	<i>parameter</i>	<i>value</i>	<i>unit</i>	<i>norm</i>	<i>comment</i>
Water absorption	24 h in water, 23°C	0.61	%	DIN EN ISO 62	(1) Corresponding means no listing at UL (yellow card). The information might be taken from resin, stock shape or estimation. Individual testing regarding application conditions is mandatory.
Water absorption	24 h in water, 80°C	1.69	%	DIN EN ISO 62	
Flammability (UL94)	corresponding to	V0		DIN IEC 60695-11-10;	1)

