

Chemical Designation

PPS (Polyphenylsulfide)

Colour

natural

Density

1.52 g/cm³

Fillers

carbon fibres

Main features

- excellent chemical resistance
- inherent flame resistance
- excellent mechanical properties
- continuous service temperature up to 150 °C

Target Industries

- automotive industry
- mechanical engineering
- oil and gas industry
- safety engineering
- sporting goods

The material is in the phase of further development. The characteristic values of this product may change.

General material information	parameter	value	unit	norm	comment
Fibre type		Carbon HT 3k		-	
Fibre architecture		Twill 2/2		-	
Fibre areal weight		200	g/m ²	-	
Fibre volume content		50	%	-	
Resin weight content		42.7	%	-	
Areal weight finished product		349	g/m ²	-	
Material widths		1270	mm	-	
ply thickness (consolidated)		0.22	mm	-	

Mechanical properties	parameter	value	unit	norm	comment
Tensile strength		680	MPa	ISO 527-4	1)
Modulus of elasticity (tensile test)		55000	MPa	ISO 527-4	2)
Flexural strength		780	MPa	ISO 14125	3)
Modulus of elasticity (flexural test)		57000	MPa	ISO 14125	4)
Compression strength		650	MPa	ISO 14126	5)
Compression modulus		51000	MPa	ISO 14126	6)

Thermal properties	parameter	value	unit	norm	comment
Glass transition temperature		90	°C	-	(1) approximate value
Melting temperature		285	°C	-	
Service temperature	short term	260	°C	-	
Service temperature	long term	230	°C	-	
Thermal expansion (CLTE)	in 0° and 90° direction	5	10 ⁻⁶ K ⁻¹	-	1)

Predrying	parameter	value	unit	norm	comment
Drying temperature		150	°C	-	
Drying time		2-3	h	-	

