

### Chemical Designation

PPSU (Polyphenylsulfone)

### Colour

red opaque

### Density

1.34 g/cm<sup>3</sup> (\*2)

### Fillers

barium sulfate

### Main features

- x-ray opaque
- very good sterilisable
- good chemical resistance
- high gamma radiation resistance
- good heat deflection temperature
- high thermal and mechanical capacity
- hydrolysis and superheated steam resistant

### Target Industries

- medical technology

General material information	parameter	value	unit	norm	comment
Diameter		1,75 +/- 0,05	mm	-	(1) standard spool body
Spool measurements	holder	Ø 52	mm	-	(2) do not dry spool >120°C
Spool measurements	width	55	mm	-	(3) Ø 1,75mm
Spool measurements	outer diameter	Ø 200	mm	-	1)
Spool Material		Polycarbonate	-	-	2)
Filament Load per Spool		500	g	-	-
Filament Length per Spool		146	m	-	3)
Mechanical properties	parameter	value	unit	norm	comment
Tensile strength	5mm/min, Orientation XY	67,6	MPa	DIN EN ISO 527-2	1) (1) (*5) , (*6)
Tensile strength	5mm/min, Orientation XZ	71,3	MPa	DIN EN ISO 527-2	2) (2) (*5) , (*6)
Tensile strength	5mm/min, Orientation ZX	68,5	MPa	DIN EN ISO 527-2	3) (3) (*5) , (*6)
Modulus of elasticity (tensile test)	5mm/min, Orientation XY	2206,0	MPa	DIN EN ISO 527-2	4) (4) (*5) , (*6)
Modulus of elasticity (tensile test)	5mm/min, Orientation XZ	2355,0	MPa	DIN EN ISO 527-2	5) (5) (*5) , (*6)
Modulus of elasticity (tensile test)	5mm/min, Orientation ZX	2311,3	MPa	DIN EN ISO 527-2	6) (6) (*5) , (*6)
Elongation at yield (tensile test)	5mm/min, Orientation XY	7,4	%	DIN EN ISO 527-2	7) (7) (*5) , (*6)
Elongation at yield (tensile test)	5mm/min, Orientation XZ	7,4	%	DIN EN ISO 527-2	8) (8) (*5) , (*6)
Elongation at yield (tensile test)	5mm/min, Orientation ZX	6,6	%	DIN EN ISO 527-2	9) (9) (*5) , (*6)
Elongation at break (tensile test)	5mm/min, Orientation XY	48,9	%	DIN EN ISO 527-2	10) (10) (*5) , (*6)
Elongation at break (tensile test)	5mm/min, Orientation XZ	80,7	%	DIN EN ISO 527-2	11) (11) (*5) , (*6)
Elongation at break (tensile test)	5mm/min, Orientation ZX	7,9	%	DIN EN ISO 527-2	12) (12) (*5) , (*6)
Elongation at yield (flexural test)	2mm/min, Orientation XY	7,3	%	DIN EN ISO 178	13) (13) (*5) , (*6)
Elongation at yield (flexural test)	2mm/min, Orientation XZ	7,4	%	DIN EN ISO 178	14) (14) (*5) , (*6)
Flexural strength	2mm/min, Orientation XY	105,0	MPa	DIN EN ISO 178	15) (15) (*5) , (*6)
Flexural strength	2mm/min, Orientation ZX	101,0	MPa	DIN EN ISO 178	16) (16) (*5) , (*6)
Modulus of elasticity (flexural test)	2mm/min, Orientation XY	2300,0	MPa	DIN EN ISO 178	17) (17) (*5) , (*6)
Modulus of elasticity (flexural test)	2mm/min, Orientation ZX	2130,0	MPa	DIN EN ISO 178	18) (18) (*5) , (*6)
Elongation at break (flexural test)	2mm/min, Orientation XY	no break	%	DIN EN ISO 178	19) (19) (*5) , (*6)
Elongation at break (flexural test)	2mm/min, Orientation ZX	no break	%	DIN EN ISO 178	20) (20) (*5) , (*6)
Thermal properties	parameter	value	unit	norm	comment
Glass transition temperature		218	°C	ASTM D 3418	1) (1) (*2)
Melting temperature		-	°C	DIN EN ISO 11357	2) (2) (*2)
Deflection temperature	HDT-A	207	°C	ISO-R 75 Method A	3) (3) (*2)
Service temperature	short term	190	°C	-	4) (4) (*2)
Service temperature	long term	170	°C	-	5) (5) (*2)
Thermal expansion (CLTE)		5,6	10 <sup>-5</sup> K <sup>-1</sup>	DIN EN ISO 11359-1;2	6) (6) (*2)
Other properties	parameter	value	unit	norm	comment
Moisture absorption		0,37	%	DIN EN ISO 62	1) (1) (*2)
Melt flow index (MFI)	365°C / 5kg	12 - 17	g/10 min	DIN EN ISO 1133	2) (2) (*2)
Processing parameter	parameter	value	unit	norm	comment
Nozzle temperature		380 - 420	°C	-	(1) required
Max. melt temperature		450	°C	-	-
Print bed temperature		160 - 230	°C	-	-
Build chamber temperature		160 - 210	°C	-	1)
Nozzle diameter		0,4	mm	-	-
Print speed		30 - 40	mm/s	-	-
Fan speed		0	%	-	-
Pre-drying	parameter	value	unit	norm	comment
Drying temperature		120	°C	-	1) (1) (*4)



For latest datasheets,  
visit our website:  
[www.facadecreations.co.uk](http://www.facadecreations.co.uk)

While the information on this data sheet is believed to be correct at the time of publication, it is the customer's responsibility to ensure the correct use and application of this product. The buyer undertakes all liability in respect of the application, processing or use of this information or product, whose quality and other properties he shall verify, or any consequence thereof.