Technical Specification Sheets

T: +44 (0) 116 289 3343 E: info@facadecreations.co.uk W: www.facadecreations.co.uk
Registered Office Address: 124 City Road, London, England, EC1V 2NX. Registered in England, Company Number: 16267073

Chemical Designation
PPSU (Polyphenylsulfone)

Colour
yellow opaque

Density
1.34 g/cm^3 (*2)

Fillers
barium sulfate

Main features
- x-ray opaque
- very good sterilisable
- good chemical resistance
- high gamma radiation resistance
- good heat deflection temperature
- high thermal and mechanical capacity
- hydrolysis and superheated steam resistant

Target Industries
- medical technology

General material information	parameter	value	unit	norm		comment
Diameter		1,75 +/- 0,05	mm	-		(1) standard spool body (2) do not dry spool >120°C (3) Ø 1,75mm
Spool measurements	holder	Ø 52	mm	-		
Spool measurements	width	55	mm	-		
Spool measurements	outer diameter	Ø 200	mm	-	1)	
Spool Material		Polycarbonate		-	2)	
Filament Load per Spool		500	g	-		
Filament Length per Spool		146	m	-	3)	

Mechanical properties	parameter	value	unit	norm		comment
Tensile strength	5mm/min, Orientation XY	63,5	MPa	DIN EN ISO 527-2	1)	(1) (*5) , (*6) (2) (*5) , (*6) (3) (*5) , (*6) (4) (*5) , (*6) (5) (*5) , (*6) (6) (*5) , (*6) (7) (*5) , (*6) (8) (*5) , (*6) (9) (*5) , (*6) (10) (*5) , (*6) (11) (*5) , (*6) (12) (*5) , (*6) (13) (*5) , (*6) (14) (*5) , (*6) (15) (*5) , (*6) (16) (*5) , (*6) (17) (*5) , (*6) (18) (*5) , (*6) (19) (*5) , (*6) (20) (*5) , (*6)
Tensile strength	5mm/min, Orientation XZ	68,0	MPa	DIN EN ISO 527-2	2)	
Tensile strength	5mm/min, Orientation ZX	65,9	MPa	DIN EN ISO 527-2	3)	
Modulus of elasticity (tensile test)	5mm/min, Orientation XY	2243,0	MPa	DIN EN ISO 527-2	4)	
Modulus of elasticity (tensile test)	5mm/min, Orientation XZ	2364,0	MPa	DIN EN ISO 527-2	5)	
Modulus of elasticity (tensile test)	5mm/min, Orientation ZX	2336,7	MPa	DIN EN ISO 527-2	6)	
Elongation at yield (tensile test)	5mm/min, Orientation XY	7,5	%	DIN EN ISO 527-2	7)	
Elongation at yield (tensile test)	5mm/min, Orientation XZ	7,1	%	DIN EN ISO 527-2	8)	
Elongation at yield (tensile test)	5mm/min, Orientation ZX	6,7	%	DIN EN ISO 527-2	9)	
Elongation at break (tensile test)	5mm/min, Orientation XY	69,1	%	DIN EN ISO 527-2	10)	
Elongation at break (tensile test)	5mm/min, Orientation XZ	82,7	%	DIN EN ISO 527-2	11)	
Elongation at break (tensile test)	5mm/min, Orientation ZX	8,7	%	DIN EN ISO 527-2	12)	
Elongation at yield (flexural test)	2mm/min, Orientation XY	7,3	%	DIN EN ISO 178	13)	
Elongation at yield (flexural test)	2mm/min, Orientation ZX	7,4	%	DIN EN ISO 178	14)	
Flexural strength	2mm/min, Orientation XY	105,0	MPa	DIN EN ISO 178	15)	
Flexural strength	2mm/min, Orientation ZX	101,0	MPa	DIN EN ISO 178	16)	
Modulus of elasticity (flexural test)	2mm/min, Orientation XY	2300,0	MPa	DIN EN ISO 178	17)	
Modulus of elasticity (flexural test)	2mm/min, Orientation ZX	2130,0	MPa	DIN EN ISO 178	18)	
Elongation at break (flexural test)	2mm/min, Orientation XY	no break	%	DIN EN ISO 178	19)	
Elongation at break (flexural test)	2mm/min, Orientation ZX	no break	%	DIN EN ISO 178	20)	

Thermal properties	parameter	value	unit	norm		comment
Glass transition temperature		218	°C	ASTM D 3418	1)	(1) (*2) (2) (*2) (3) (*2) (4) (*2) (5) (*2) (6) (*2)
Melting temperature		-	°C	DIN EN ISO 11357	2)	
Deflection temperature	HDT-A	207	°C	ISO-R 75 Method A	3)	
Service temperature	short term	190	°C	-	4)	
Service temperature	long term	170	°C	-	5)	
Thermal expansion (CLTE)		5,6	10^{-5} K^{-1}	DIN EN ISO 11359-1;2	6)	

Other properties	parameter	value	unit	norm		comment
Moisture absorption		0,37	%	DIN EN ISO 62	1)	(1) (*2) (2) (*2)
Melt flow index (MFI)	365°C / 5kg	12 - 17	g/10 min	DIN EN ISO 1133	2)	

Processing parameter	parameter	value	unit	norm		comment
Nozzle temperature		380 - 420	°C	-		(1) required
Max. melt temperature		450	°C	-		
Print bed temperature		160 - 230	°C	-		
Build chamber temperature		160 - 210	°C	-	1)	
Nozzle diameter		0,4	mm	-		
Print speed		30 - 40	mm/s	-		
Fan speed		0	%	-		

Predrying	parameter	value	unit	norm		comment
Drying temperature		120	°C	-	1)	(1) (*4)

While the information on this data sheet is believed to be correct at the time of publication, it is the customer's responsibility to ensure the correct use and application of this product. The buyer undertakes all liability in respect of the application, processing or use of this information or product, whose quality and other properties he shall verify, or any consequence thereof.