

Chemical Designation

PEEK (Polyetheretherketone)

Colour

black

Density

1.39 g/cm³

Fillers

carbon fibres

Main features

- very high stiffness
- very high strength
- good wear resistance
- very good heat resistance
- high creep resistance
- very good chemical resistance
- hydrolysis and superheated steam resistant
- for injection moulding

Target Industries

- mechanical engineering
- oil and gas industry
- chemical technology
- automotive industry
- vacuum technology

| <i>Mechanical properties</i> | <i>parameter</i> | <i>value</i> | <i>unit</i> | <i>norm</i> | <i>comment</i> |
|--------------------------------------|------------------|-----------------|-------------------|--------------------|----------------|
| Tensile strength | | 242 | MPa | DIN EN ISO 527-1 | |
| Modulus of elasticity (tensile test) | | 24400 | MPa | DIN EN ISO 527-1 | |
| Elongation at break (tensile test) | | 1,8 | % | DIN EN ISO 527-1 | |
| Impact strength (Charpy) | | 44 | kJ/m ² | DIN EN ISO 179-1eU | |
| <i>Thermal properties</i> | <i>parameter</i> | <i>value</i> | <i>unit</i> | <i>norm</i> | <i>comment</i> |
| Glass transition temperature | | 143 | °C | - | 1) |
| Melting temperature | | 343 | °C | - | 2) |
| Heat distortion temperature | | 332 | °C | ISO-R 75 Method A | 3) 4) |
| Service temperature | long term | 260 | °C | - | 3) |
| Service temperature | short term | 300 | °C | - | 4) |
| <i>Electrical properties</i> | <i>parameter</i> | <i>value</i> | <i>unit</i> | <i>norm</i> | <i>comment</i> |
| surface resistivity | | 10 ⁵ | Ω | DIN EN 61340-2-3 | |
| volume resistivity | | 10 ⁴ | Ω*cm | DIN EN 61340-2-3 | |
| <i>Other properties</i> | <i>parameter</i> | <i>value</i> | <i>unit</i> | <i>norm</i> | <i>comment</i> |
| Molding shrinkage | longitudinal | 0,3 | % | DIN EN ISO 294-4 | |
| Molding shrinkage | transverse | 0,9 | % | DIN EN ISO 294-4 | |
| <i>Processing parameter</i> | <i>parameter</i> | <i>value</i> | <i>unit</i> | <i>norm</i> | <i>comment</i> |
| processing temperatures | | 360 - 400 | °C | - | |
| Mould temperature | | 160 - 210 | °C | - | |

→ This material can be processed as a thermoplastic taking the normal technical provisions into account. The above mentioned information refers exclusively to the injection moulding process.

→ Processing should be carried out as gently as possible, in order to maintain the maximum fibre length in the component. Back pressure and injection rate should be adjusted to the component geometry accordingly. The optimum processing temperature depends upon the respective geometry of the moulded part and can be different from machine to machine.

| <i>Predrying</i> | <i>parameter</i> | <i>value</i> | <i>unit</i> | <i>norm</i> | <i>comment</i> |
|---------------------------------------|------------------|--------------|-------------|-------------|----------------|
| Permissible residual moisture content | | < 0,1 | % | - | |
| Drying temperature | | 120 - 140 | °C | - | |
| Drying time | | 4 | h | - | |

