Technical Specification Sheets

T: +44 (0) 116 289 3343 E: info@facadecreations.co.uk W: www.facadecreations.co.uk
Registered Office Address: 124 City Road, London, England, EC1V 2NX. Registered in England, Company Number: 16267073

Chemical Designation
PEEK (Polyetheretherketone)

Colour
black opaque

Density
1.3 g/cm^3 (*2)

Main features
- inherent flame retardant
- very good chemical resistance
- good slide and wear properties
- good heat deflection temperature
- resistance against high energy radiation
- hydrolysis and superheated steam resistant

Target Industries
- electronics
- food technology
- automotive industry
- chemical technology
- mechanical engineering
- aircraft and aerospace technology

General material information	*parameter*	*value*	*unit*	*norm*		*comment*
Diameter		1,75 +/- 0,05	mm	-		(1) standard spool body (2) do not dry spool >120°C (3) Ø 1,75mm
Spool measurements	holder	Ø 52	mm	-		
Spool measurements	width	55	mm	-		
Spool measurements	outer diameter	Ø 200	mm	-	1)	
Spool Material		Polycarbonate		-	2)	
Filament Load per Spool		500	g	-		
Filament Length per Spool		149	m	-	3)	

Mechanical properties	*parameter*	*value*	*unit*	*norm*		*comment*
Tensile strength	5mm/min, Orientation XY	84,4	MPa	DIN EN ISO 527-2	1)	(1) (*5) , (*6) (2) (*5) , (*6) (3) (*5) , (*6) (4) (*5) , (*6) (5) (*5) , (*6) (6) (*5) , (*6) (7) (*5) , (*6) (8) (*5) , (*6) (9) (*5) , (*6) (10) (*5) , (*6) (11) (*5) , (*6) (12) (*5) , (*6)
Tensile strength	5mm/min, Orientation XZ	94,8	MPa	DIN EN ISO 527-2	2)	
Tensile strength	5mm/min, Orientation ZX	85,6	MPa	DIN EN ISO 527-2	3)	
Modulus of elasticity (tensile test)	5mm/min, Orientation XY	3365,0	MPa	DIN EN ISO 527-2	4)	
Modulus of elasticity (tensile test)	5mm/min, Orientation XZ	3950,0	MPa	DIN EN ISO 527-2	5)	
Modulus of elasticity (tensile test)	5mm/min, Orientation ZX	3700,8	MPa	DIN EN ISO 527-2	6)	
Elongation at yield (tensile test)	5mm/min, Orientation XY	6,5	%	DIN EN ISO 527-2	7)	
Elongation at yield (tensile test)	5mm/min, Orientation XZ	6,7	%	DIN EN ISO 527-2	8)	
Elongation at yield (tensile test)	5mm/min, Orientation ZX	4,5	%	DIN EN ISO 527-2	9)	
Elongation at break (tensile test)	5mm/min, Orientation XY	29,9	%	DIN EN ISO 527-2	10)	
Elongation at break (tensile test)	5mm/min, Orientation XZ	17,7	%	DIN EN ISO 527-2	11)	
Elongation at break (tensile test)	5mm/min, Orientation ZX	5,0	%	DIN EN ISO 527-2	12)	

Thermal properties	*parameter*	*value*	*unit*	*norm*		*comment*
Glass transition temperature		143	°C	ASTM D 3418	1)	(1) (*2) (2) (*2) (3) (*2) (4) (*2) (5) (*2) (6) (*2)
Melting temperature		343	°C	DIN EN ISO 11357	2)	
Deflection temperature	HDT-A	162	°C	ISO-R 75 Method A	3)	
Service temperature	short term	300	°C	-	4)	
Service temperature	long term	260	°C	-	5)	
Thermal expansion (CLTE)		5	10^{-5} K $^{-1}$	DIN EN ISO 11359-1;2	6)	

Other properties	*parameter*	*value*	*unit*	*norm*		*comment*
Moisture absorption		0,03	%	DIN EN ISO 62	1)	(1) (*2) (2) (*2) (3) (*2)
Flammability (UL94)	125x13x1,5mm	V0		DIN IEC 60695-11-10;	2)	
Melt flow index (MFI)	380°C / 5kg	8	g/10 min	DIN EN ISO 1133	3)	

Processing parameter	*parameter*	*value*	*unit*	*norm*		*comment*
Nozzle temperature		420 - 440	°C	-		(1) required
Max. melt temperature		470	°C	-		
Print bed temperature		160 - 250	°C	-		
Build chamber temperature		160 - 230	°C	-	1)	
Nozzle diameter		0,4	mm	-		
Print speed		20 - 30	mm/s	-		
Fan speed		0	%	-		

Predrying	*parameter*	*value*	*unit*	*norm*		*comment*
Drying temperature		120	°C	-	1)	(1) (*4)
Drying time		8	h	-		

While the information on this data sheet is believed to be correct at the time of publication, it is the customer's responsibility to ensure the correct use and application of this product. The buyer undertakes all liability in respect of the application, processing or use of this information or product, whose quality and other properties he shall verify, or any consequence thereof.